

ABSTRACT

A method of production of a rubbery polymer by adding a coagulating agent to a polymer latex to make the rubbery polymer ingredient coagulate, the method of production of a rubbery polymer having a step of using a crusher pump to make the rubbery polymer ingredient coagulate to obtain a crumb slurry, using as the crusher pump a pump having a head of 10 m or more. According to this invention, in a method of production of a rubbery polymer by adding a coagulating agent to a polymer latex to make the rubbery polymer ingredient coagulate, an improvement of the operation efficiency and a reduction of the production process and production equipment are made possible and a reduction of the equipment costs and a reduction of the production costs can be achieved.